

DELLA BOYOMA

“Safety is non-negotiable”

TANNING TARGET

Firmness – No stretch – No elongation – No breaking

Mineral tanning, double mineral/vegetable tanning, wax/tallow nourishment.

FINISHING TARGET

Natural

Aniline finish, wax finish, grain and flesh side hardener.

HORSE EQUIPMENT

Hard Stretched Leather





ENRICH YOUR LEATHER

COLORS

- Dyed through or surface dyed
- Shiny / matt

FEEL

- Very hard - 100% mineral tanning
- Semi hard - double tanning (veg & min)

GRAIN

- Natural grain
- Grain prints available

THICKNESS

- 4/4,5mm
- 4,5/5mm
- 4,8+ mm

HIDES

- 1/3 Butt


CUTTING SERVICE

We provide a cutting service to offer 100% usable leather avoiding any waste for the customer.
No waste means more savings.

LABELS, ORIGIN & TRACEABILITY

- Responsibly farmed bull leather
- 100% European origin
- Belgium Artisan Certified
- Sustainable water consumption
- Renewable chemicals REACH compliance





Stretching on 1/3 croupions/butts, allows to stretch the stiffer fibres on the spine and the looser ones on the sides to the same maximum firmness.

There is no compromise on safety. We provide an overall homogeneous stretch.

TEST TABLE

	METHOD			SAMPLE		RESULT DELLA	RESULT BOYOMA
Veslic rub fastness dry	1kg/100 c	ISO 11640		ISO 2419		2	3/4
Veslic rub fastness wet	1kg/25 c	ISO 11640		ISO 2419		3	3/4
Tear load			TVS 10KN100		25x200 mm	493kg	426,5kg
Tear resistance			TVS 10KN100		25x200 mm	4,93kg/mm ²	3,55kg / mm ²
Elongation at rupture			TVS 10KN100		25x200 mm	60,2mm	62,2mm
Tensile endurance elongation	75-0,5kg/1000 c	ISO 3376	TVS 10KN100	ISO 2419	25x200 mm	1,28%	4,2%

