

data sheet

Art.: Salpa synderme - Épaisseur 0.4mm

thickness and tolerance :	0,4 /10 mm	± 1/10 mm
weight :	0,320 Kg/m ²	± 3%
width :	145 cm	
application :	PE	reinforcement
composition		
leather shavings :	64%	± 4%
latex content :	18%	± 10%
water / humidity	10%	± 10%
fats - retannings natural based	8%	± 10%

Technical data			test method
Average Elongation (ref.thickness 1 mm.)	≥ 20	%	UNI EN 3376:2011
Sampled and/or Custom colour tone tolerance	ND	Δeab	UNI EN ISO 7724
Accelerate weathering test in dark conditions	ND	ΔE	UNICHIM 2195-70 scala grigi /grey scale 4
Tensile strenght and elongation	8	N/mm ²	UNI EN ISO 3376
Colorfastness to rubbing dry & wet	ND	dry rubbings	UNI EN ISO 11640
	ND	wet rubbings	
Tear strenght	≥ 15	N/mm ²	UNI EN ISO 3377:2006
determination of dimensional stability	1	%	UNI 8481

Certificazioni / Certifications



GRS CERTIFICATION - GLOBAL RECYCLE STANDARD

The Institute for "Ethical and Environmental Certification", authorized by the American Society Textile Exchange

The material complies with the following standard and regulation : Washington Convention (CITES) of 03/03/1973 and its corrections - Reach Regulation and its integrations - for further information please contact us.

Deco Cuir is not responsible for the final use and destination of the product, it is always suggested to carry out the tests and evidence necessary to determine the final applicability.

Storage and Usage

Given the natural origin of its composition, bonded leather must be stored in places granting the preservation of the percentage of humidity of the material, avoiding sudden changes; we suggest to store in indoor premises at a temperature between 18° and 30° with humidity between 30% and 65%. **The thermo-retractable polyethylene packaging** plays a protective action of the material, it is advisable to keep the material well packaged when not in use.

The peculiarity of our Standard Quality is the dry hand that lends itself for reinforcements and support to the artifact.

It can be matched with other materials such as leather, synthetics, tissue ect.

We suggest not to expose the material to direct or indirect sunlight for prolonged periods, bonded leather is made of animal fibers and it can be influenced by external stresses, latex that has a binding function, being a natural product, after a period of stability begins its natural aging process, we suggest to use the material within 6-12 months.